

DuPont™ Cyrel® DFM

MEDIUM DUROMETER HIGH RESOLUTION DIGITAL PLATE
FOR CYREL®FAST

DuPont Packaging Graphics

To help our customers gain competitive advantage in the global packaging graphics value chain.

DuPont Packaging Graphics continues to be a global technology leader in supplying flexographic printing systems. Our scientists continue to develop unique solutions based on new technologies to help our customers expand their business by taking advantage of new profitable packaging printing opportunities.

DuPont Packaging Graphics portfolio of products includes Cyrel® brand photopolymer plates (analog and digital), Cyrel® platemaking equipment, Cyrel®round sleeves, Cyrel® plate mounting systems and the revolutionary Cyrel®FAST thermal system.

**Cyrel®FAST plates in one hour or less!
Cyrel® DFM is the medium durometer plate for DuPont's thermal platemaking process, designed to meet the needs of high quality flexo with fine halftone, linework and solids.**

Applications

- Flexible packaging
- Tag & Label
- Envelopes
- Carrier bags
- Folding cartons
- Pre-print liner
- Beverage cartons

Product Features

- Extremely rapid access time – thanks to thermal plate processing without drying



DuPont™ Cyrel® DFM

- Excellent ink transfer permits superior printing uniformity
- Higher durability for long print runs
- High exposure resolution results in better quality reproduction
- Image relief is clean and sharp
- Exceptional thickness uniformity – No plate swelling during platemaking
- Less make ready time on press
- High resistance to ozone and white light results in excellent storage flexibility

Printing ink and solvent compatibility

Cyrel® DFM offers excellent compatibility with UV, solvent-based and water-based inks.

Platemaking

The Cyrel®FAST thermal developer allows the production of Cyrel®FAST finished plates in less than one hour, making it the ideal just-in-time platemaking system for a market that demands quick turnaround and high quality. The Cyrel®FAST thermal developer delivers outstanding plate qual-

ity and uniformity. This processor has the ability to produce a finished plate without solvent washout. The Cyrel® EC/LF for exposing and light-finishing plates is available to complement the Cyrel®FAST thermal developer.

Process of use

DFM is designed to work with Cyrel®FAST thermal platemaking. Expose the plate through the back to establish the floor and maximise sensitivity. Back exposure varies according to relief required. Remove the protective coversheet, and image the plate with the Cyrel® Digital Imager (CDI). Expose the front of the plate surface. Process the plate in the Cyrel®FAST thermal developer. Finish the plate in a light finisher to eliminate surface tackiness. Post-expose the plate to ensure complete polymerization.

Mounting

Cyrel® Microflex mounting devices are recommended for mounting Cyrel® DFM



The miracles of science™

DuPont Packaging Graphics
“Advancing Flexography”

plates. The double sided adhesive should first be applied to the cylinder or sleeve – not the plate – to ensure easier and precise laydown. The polyester base will maintain accurate register even with large plates.

Storage – Raw Material

Store unexposed plates in a cool area, away from direct sources of heat. Humid-

ity control is not required. Cyrel® DFM is foam interleaved to provide maximum protection of the plate after manufacture, and during transportation and storage. Plates should be stacked flat. Plates should not be exposed to direct sunlight or excessive white light. Continuous exposure to very high ozone concentrations should be avoided.

Handling – Raw Material

Cyrel® DFM plates should be handled under UV free light; e.g. fluorescent tubes covered with amber sleeves.

Storage – Finished Plates

After printing, plates should be thoroughly cleaned with compatible solvent before storing. They may be stored on cylinders, sleeves or demounted and stored flat.

Available plate sizes				
	Cyrel® DFM 45 Thickness 0.045 inch	Cyrel® DFM 67 Thickness 0.067 inch	Cyrel® DFM 100 Thickness 0.1 inch	Cyrel® DFM 112 Thickness 0.112 inch
25 inch x 30 inch	●	●		
30 inch x 42 inch	●	●		
35 inch x 47 inch	●	●	●	●
42 inch x 60 inch	●	●	●	●

Technical Data				
Durometer	70 Sh A	58 Sh A	47 Sh A	48 Sh A
Image Reproduction	1 – 98% 175 L/Inch	1 – 98% 175 L/Inch	1 - 98% 175 L/Inch	1 – 98% 175 L/Inch
Minimum positive line width	3 mil	3 mil	3 mil	3 mil
Minimum isolated dot size	5 mil	5 mil	5 mil	5 mil
Relief Depth	.018 – .023 inch	.018 – .023 inch	.020 – .028 inch	.020 – .028 inch

All technical information set out herein is provided free of charge and is based on technical data, which DuPont believes to be reliable. It is intended for use by persons having skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use are outside of our control we make no warranties express or implied in relation thereto and therefore cannot accept any liability in connection with any use of this information. Nothing herein is to be taken as a license to operate under, or a recommendation to infringe any patents.

United States

DuPont Customer Technology Center
Chestnut Run Plaza, Bldg. 702
Wilmington, DE 19880-0702
800.345.9999

Canada

DuPont Packaging Graphics
P.O. Box 2200, Streetsville
Mississauga, Ontario Canada, L5M 2H3
905.821.5042

To learn more, visit www.cyrel.dupont.com
or contact your Cyrel® specialist



The miracles of science™